



# Silicones, Inc.

P.O. Box 363  
High Point, NC 27261  
Tel: 336-886-5018  
Fax: 336-886-7122  
www.silicones-inc.com

*RTV-2 Silicones Since 1974*

## GI-765

### Product Information

#### General Information

**GI-765** is a thixotropic (resistant to flow) tin catalyzed silicone designed to be used when painting *or* spraying onto vertical surfaces. **GI-765** does not contain the mold rotting thixo-additives widely used today, but offers the end user the same ease of use and detail reproducibility. When catalyzed with one of our library life extending catalysts (see supplemental products) and stored correctly, a longer life of the cured mold should be expected. Its high tear strength, elongation and tensile strength make it an excellent choice for any mold making application. It is also resistant to inhibition by most common mold making substrates, eliminating the need to use mold sealers.

#### Typical Properties

##### Uncatalyzed Compound

<b>Color</b>	Base: White	Activator: Teal
<b>Viscosity (cps)</b>	Base: 425,000 - 500,000	Activator: 900 - 1100
<b>Mixing Ratio (B/A)</b>	By weight: 100 / 10	By volume: 100 / 11.1
<b>Mixed Viscosity</b>	400,000 - 450,000	
<b>Working Time</b>	1 to 1.5 hours	
<b>Cure Time</b>	16 - 18 hours	
<b>Shelf Life</b>	6 months	

##### Vulcanized (cured) Properties (7 days @ 70° F / 50% relative humidity)

<b>Shore A Hardness (<math>\pm 4</math>)</b>	One day: 25	7 Days: 28
<b>Tear Resistance (ASTM D624)</b>	120 $\pm$ 10 ppi	
<b>Tensile Strength (ASTM D412)</b>	375 $\pm$ 25 psi	
<b>Elongation (ASTM D412)</b>	400 $\pm$ 50 %	
<b>Service Temperature (<math>^{\circ}</math> F)</b>	-60 to 350	
<b>Shrinkage</b>	0.10 %	
<b>Specific Gravity</b>	1.10	
<b>Coverage (in<sup>3</sup> / lb)</b>	25.2	

*The information contained in this data sheet is, to our best knowledge, true and accurate, but all recommendations or suggestions are made without guarantee. Since the conditions of use are beyond our control, Silicones, Inc. disclaims any liability incurred in connection with the use of our products and information contained herein.*