



Silicones, Inc.

P.O. Box 363
High Point, NC 27261
Tel: 336-886-5018
Fax: 336-886-7122
www.silicones-inc.com

RTV-2 Silicones Since 1974

P-125

Product Information

General Information

P-125 is a translucent, high tear strength, platinum-catalyzed, RTV-2 silicone rubber, which was designed for casting parts where visual inspection is required. It is easy to mix and de-air, and will cure with virtually no shrinkage. The speed at which the rubber hardens can be dramatically accelerated with heat or with **Pt Accelerator** at room temperature. Addition-cure two-component silicone rubbers exhibit excellent chemical and heat resistance, but may show some inhibition sensitivity. **P-125** is extremely useful for prototype applications where superior mechanical properties are required.

Typical Properties

Uncatalyzed Compound

Color	Base: Translucent	Activator: Clear
Viscosity (cps)	Base: 160,000-180,000	Activator: 1,000-2,000
Mixing Ratio (B/A)	By weight: 100 / 10	By volume: 100 / 10.9
Viscosity (cps)	Mixed: 90,000-110,000	
Working Time	1 to 2 hours	
Cure Time	16-24 hours	
Shelf Life	6 months	

Vulcanized (cured) Properties (7 days @ 70° F / 50% relative humidity)

Shore A Hardness (±4)	One day: 40	7 Days: 40
Tear Resistance (ASTM D624)	90 ± 15 pli	
Tensile Strength (ASTM D412)	700 ± 50 psi	
Elongation (ASTM D412)	250 ± 50 %	
Service Temperature (° F)	-60 to 600	
Shrinkage	<i>nil</i>	
Specific Gravity	1.09	
Coverage (in³ / lb)	25.6	
Dielectric Strength (volts/mil)	500	
Dielectric Constant (@ 100 HZ)	2.9	
Dissipation Factor (@ 100 HZ)	0.003	
Volume Resistivity (ohms/cm)	1 x 10 ¹⁵	

The information contained in this data sheet is, to our best knowledge, true and accurate, but all recommendations or suggestions are made without guarantee. Since the conditions of use are beyond our control, Silicones, Inc. disclaims any liability incurred in connection with the use of our products and information contained herein.