



Silicones, Inc.

P.O. Box 363
High Point, NC 27261
Tel: 336-886-5018
Fax: 336-886-7122
www.silicones-inc.com

RTV-2 Silicones Since 1974

P-10, P-15 and P-20

Product Information

General Information

P-10, P-15 and P-20 RTV silicone rubbers are two-component, platinum-catalyzed systems that cure at room temperature. All of these materials have low viscosity, high elongation, high tear strength and low durometer. They are easy to mix and de-air, and will cure with virtually no shrinkage. The speed at which the rubber hardens can be dramatically accelerated with heat or with **Pt Accelerator** at room temperature. Addition-cure two-component silicone rubbers exhibit excellent chemical and heat resistance, but may show inhibition sensitivity. **P-10, P-15 and P-20** offer excellent release properties and are extremely useful for casting complex shapes, animatronic skins, or any application where exceptional flexibility and tear resistance are required.

Typical Properties

Uncatalyzed Base	P-10B	P-15B	P-20B
Color	Pink or Translucent	Pink or Translucent	Pink or Translucent
Viscosity (\pm 5,000 cps)	15,000	30,000	30,000
Mixing Ratio (B/A)			
By weight:	100/10	100/10	100/10
By volume:	100/10.9	100/10.9	100/10.9
Mixed Viscosity (\pm 5,000 cps)	10,000	8,000	20,000
Working Time (Hours)	1 to 2	1 to 2	1 to 2
Cure Time (Hours)	16 to 18	16 to 18	16 to 18
Shelf Life (Months)	6	6	6

Vulcanized (cured) Properties (7 days @ 70° F / 50% relative humidity)

Shore A Hardness (\pm 4)

One day / 7 Days:	10 / 12	15 / 18	20 / 22
Tear Resistance , ppi (ASTM D624)	75 \pm 25	100 \pm 25	120 \pm 25
Tensile Strength , psi (ASTM D412)	350 \pm 50	475 \pm 50	525 \pm 50
% Elongation (ASTM D412)	450 \pm 50	460 \pm 50	425 \pm 50
Service Temperature , °F	-60 to 550	-60 to 550	-60 to 550
Shrinkage	nil	nil	nil
Specific Gravity	1.08	1.08	1.08
Coverage , in ³ / lb	25.6	25.6	25.6

The information contained in this data sheet is, to our best knowledge, true and accurate, but all recommendations or suggestions are made without guarantee. Since the conditions of use are beyond our control, Silicones, Inc. disclaims any liability incurred in connection with the use of our products and information contained herein.