



Silicones, Inc Si-mplication

Platinum Silicone Gels

The following 2-part, room temperature cure, addition reacted silicone gels were designed for potting and encapsulating as well as providing superior damping characteristics. Can also be used in conjunction with platinum cured special effects silicones to produce realistic simulations of living tissue.

	XP-574	P-157	P-429	XP-831	XP-832
Mix Ratio	10:1	10:1	1:1	1:1	1:1
Work Time (hours)	2 - 4	2 - 4	2 - 4	2 minutes	1:30 - 2:30
Demold (hours)	18 - 24	18 - 24	18 - 24	5 minutes	6
Color	Clear	Clear	Clear	Clear	Translucent

The information contained in this product information sheet is based on sources believed to be accurate. It is offered in good faith, but without guarantee since the conditions of use are beyond our control. All risks of use are assumed by the user.

Silicones, Inc. 211 Woodbine St. High Point, NC 27261 1.800.533.8709
Proudly made in the USA